

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : D06N 5/00, E04D 5/06, C08L 95/00	A1	(11) International Publication Number: WO 00/44975 (43) International Publication Date: 3 August 2000 (03.08.00)
(21) International Application Number: PCT/CA00/00069 (22) International Filing Date: 26 January 2000 (26.01.00) (30) Priority Data: 60/117,427 27 January 1999 (27.01.99) US (71) Applicants (for all designated States except US): POLYPHALT INC. [CA/CA]; Suite 125, 270 Yorkland Boulevard, Toronto, Ontario M2J 5C9 (CA). ZHANG, Yan-Ping [CA/CA]; 24 Chiltern Hill, Richmond Hill, Ontario L4B 3B8 (CA). (72) Inventor; and (75) Inventor/Applicant (for US only): LIANG, Zhi, Zhong [CA/CA]; 24 Chiltern Hill, Richmond Hill, Ontario L4B 3B8 (CA). (74) Agent: STEWART, Michael, I.; Sim & McBurney, 6th floor, 330 University Avenue, Toronto, Ontario M5G 1R7 (CA).		(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: MODIFIED BITUMINOUS COMPOSITION FOR ROOF MEMBRANES (57) Abstract Roofing membranes are provided with both high stiffness at high temperature (greater than 110 °C) and good flexibility at low temperature (less than -20 °C). Bituminous compositions may be more effectively used in such membranes at lower elastomer concentration than currently practiced, using conventional cross-linking reagents to prepare the modified bituminous compositions with a range of viscosities that are readily processed as compared with conventional non-cross-linked systems.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

TITLE OF INVENTIONMODIFIED BITUMINOUS COMPOSITION FOR ROOF MEMBRANESFIELD OF INVENTION

5 The present invention relates to waterproofing products, particularly elastomer-modified roof membranes using thermoplastic rubber (TR) modified bituminous compositions with an improved cost/performance balance.

BACKGROUND TO THE INVENTION

10 Bitumen is an excellent waterproofing material that has long been used in roofing applications. It is easy to apply and cheap. Roofing-grade bitumens (usually known as oxidized or 'blown' bitumen) have been used successfully for more many decades.

15 However, air-blown bitumens cannot cope with the demands of modern roofs: roofing felts need to last longer than ever and to be stable under the very varied conditions that exist worldwide. Modern roofs tend to be lighter than their predecessors, and better insulated, which widens even further the temperature range to which the surface is subject.

20 Such demands triggered the introduction of bituminous roofing membranes modified with various polymers about 20 to 30 years ago. Although use of polymer-modified bitumen membranes has become very widespread and, in some regions even more common than air-blown bitumen, only two polymer types have yet achieved significant commercial success in bituminous roofing applications, namely thermoplastic polyolefin ('plastomer') and thermoplastic rubbers (TRs). Amorphous (or atactic) polypropylene (APP) is the most prominent plastomer. TRs are represented almost exclusively by the styrene-butadiene-styrene (SBS) triblock copolymers.

25 Field studies and well documented application histories have helped the roofing industry to appreciate the improved properties and long-term performance of SBS-modified bitumen membranes.

30 The roofing industry, however, is looking more than ever to optimize the cost-performance balance of their modified bitumen roofing products. In practice, this means that the manufacturers of SBS modified roofing membranes aim to use the lowest amount of SBS copolymer possible without jeopardizing membrane properties and characteristics.

Conventional practice involves using SBS as a modifier at loading levels generally from about 10 to about 15 wt% of the bitumen, typically about 12% to 14 wt%. It has been found, when the bitumen is modified with this level of SBS, the bitumen goes through a phase inversion (the change of a compound into an isometric form) in which its characteristics change to those of the rubber additives. This results in a bituminous membrane with an excellent balance of flexibility at cold temperatures (i.e. below -20°C) and high flow resistance at high temperatures (i.e. above 110°C). Below this range of SBS loading, the modified membranes tend to fail the above performance targets and other criteria that may be specified by the relevant roofing authorities.

An objective of this invention is to develop and manufacture SBS-modified roofing sheets using a lower amount of SBS co-polymer without jeopardizing performance criteria of the products or to achieve a better performance at the same loading level with respect to conventional SBS-modified roofing sheets.

It has been recognized that bitumens are complex mixtures of hydrocarbon molecules, ranging from low molecular weight oil (maltene fraction) to heavy, polymeric-type molecules (asphaltenes). Bitumen-polymer blending has undergone years of research and practical development. More than ten types of SBS copolymers have found use in modified bitumens, and all differ in composition and molecular structure. In roofing sheet design, the bitumen type is one of most significant variables and proper selection is considered highly important.

For roofing membrane applications, in addition to SBS polymers and asphalt, other ingredients including fillers, such as, limestone-CaCO₃, must be incorporated into the blend. The fillers make up as much as 15% to 30% by wt of the compound.

Therefore, SBS and filler together blended into the bitumen binder determine the rheological behavior of the modified bitumen. The modified bitumen is then coated on a polyester fiber mat or glass fiber mat. These membranes may, if desired, be coated with granules to provide enhanced properties, such as resistance to UV degradation.

According to the present invention, in-situ vulcanization of SBS copolymer into filler-filled bitumen matrix using conventional cross-linking reagents is employed to more effectively use the elastomer without jeopardizing the characteristics of the modified roofing membrane.

It has been recognized, however, that the prior art that the technique of the in-situ cross-linking of the elastomer has been applied for the paving grade modified bitumen products where SBS is used in relatively lower amounts, generally in a range from 2 to 5%, in which the bitumen behavior predominates.

Accordingly, in one aspect of the present invention, there is provided a roofing membrane having cold flexibility below about -20°C , preferably below about -25°C , and high flow resistance (stiffness) above about 110°C , preferably above about 120°C . This membrane comprises a matrix-filled fibrous substrate and a filled elastomer-modified bituminous composition comprising about 10 to about 30 wt% of a mineral filler and a bituminous composition comprising bitumen and about 8 to 15 wt% of said bitumen of an elastomer having a conjugated diene structure cross-linked to an extent to permit a reduction of about 10 to 20 wt% in the amount of elastomer in the bituminous composition for the

same low and high temperature properties or a concomitant improvement in low and high temperature properties at the same amount of elastomer.

In the present invention, the elastomer modifier may be a diene rubber or butadiene based polymer or co-polymer, preferably a styrenic elastomer, such as a styrene-butadiene random copolymer (SBR), a di-block copolymer (SB) or a tri-
5 block copolymer (SBS) or a combination thereof. As mentioned previously, elastomers having a conjugated diene structure, namely SBS, have conventionally been used in an amount of about 10 to about 15 wt%, typically about 12 to about 14 wt%. By effecting cross-linking according to the invention, the amount of such
10 elastomer employed may be reduced by about 10 to 20% without any loss of low temperature flexibility as compared to the non-cross-linked composition. Similarly, at the same loading level as the non-cross-linked composition, improvements in both low temperature and high temperature performance are achieved in comparison to the non-cross-linked composition.

15 The cross-linking reagents used in this invention may be different types of reagents among those conventional chemical additives used in bituminous systems, such as elemental sulfur, a sulfur based vulcanization system and/or a phenol-aldehyde resin based cross-linking system.

As may be seen from the experimental results herein, differing amounts of
20 cross-linking reagent are required when a different type of cross-linking reagent is used according to the process procedures of the invention. In general, when sulfur is used for cross-linking, the amount employed is about 0.05 to about 0.2 wt%, preferably about 0.1 to about 0.15 wt% of the bitumen composition. When a phenol-formaldehyde resin is used for cross-linking, the amount employed is about
25 0.1 to about 0.25 wt%, preferably about 0.15 to about 0.20 wt%, of the bitumen composition. The compositions employed need to be adjusted based on the reagent type to achieve the corresponding performance of bituminous compositions modified using another cross-linking agent.

A key feature of the present invention is the manner in which the cross-
30 linking is effected. Only small amounts of cross-linking agents are employed, as discussed above. If too much cross-linking agent is employed in an attempt to reduce the amount of elastomer, then the low temperature flexibility will be

impaired and there is a risk of gelation. If too little cross-linking agent is employed, then the desired high temperature stiffness level cannot be achieved.

In order to achieve the desired low and high temperature properties, it is important that oxidation of the system is minimized during cross-linking. The ingestion of ambient air into the bitumen composition during the cross-linking should be minimized. Such minimization may be effected in any convenient manner, depending on the configuration of the manufacturing system. For example, on a laboratory scale, oxidation of the system is minimized by maintaining the system quiescent by controlling the level of agitation such as to provide a minimum vortex during a conditioning step. On a plant scale, mixing may be continued provided that such mixing does not result in any significant degree of incorporation of ambient air. Alternatively, a form of blanketing the material with nitrogen or other suitable materials can also serve the same purpose.

Accordingly, in another aspect of the present invention, there is provided a method of forming a roofing membrane comprising a fibrous substrate and a filled bituminous composition, which comprises:

- (a) fully dispersing into bitumen an elastomer having a conjugated diene structure in an amount of about 8 to about 13 wt% of the bitumen,
- (b) dispersing a cross-linking reagent for said elastomer in a predetermined amount depending on the reagent used,
- (c) permitting said cross-linking reagent to cross-link said elastomer while minimizing the incorporation of air into the composition,
- (d) blending a mineral filler in an amount of about 10 to about 30 wt% of the composition to provide a filled bituminous composition, and
- (e) forming a roofing membrane from said filled bituminous composition having about 10 to 20 wt% less elastomer in the bitumen for the same low and high temperature properties or a concomitant improvement in low and high temperature properties for the same amount of elastomer.

The low temperature and high temperature properties of the roofing membrane may be in accordance with any relevant specification required for such

roofing products. For example, the products of the invention may meet the standards set by the European Union in its "Special Directives for the Assessment of Reinforced Homogeneous Waterproof Coverings of Styrene-Butadiene-Styrene (SBS) Elastomer Bitumen" of August 1984 (MDAT No. 31:1984).

5

GENERAL DESCRIPTION OF INVENTION

The term "bitumen" used herein means a class of black or dark-colored (solid, semi-solid or viscous) cementitious substances, natural or manufactured, composed principally of high molecular weight hydrocarbons of which asphalts, tars, pitches and asphaltites are typical. The term "asphalt" used herein means a
10 dark, brown to black, cementitious material, solid or semi-solid in consistency, in which the predominating constituents are bitumens that occur in nature, as such, or are obtained as residue in petroleum refining.

The bitumens which may be used in the present invention vary widely in softening point, generally from about 20° to 65°C, preferably about 25° to 55°C.
15 The bitumen may comprise about 75 to about 90 wt% of the total composition, preferably about 85 to about 92 wt% of the total composition.

The elastomers which may be used in the present invention have a conjugated diene structure and may vary from elastomeric polymers to elastomeric copolymers or thermoplastic elastomers. The elastomeric copolymers
20 or thermoplastic elastomers. The elastomeric polymers may be those conjugated diene polymers selected among butadiene, isoprene and their functionalized polymers, such as those with halogenated or carboxylated groups. The elastomeric copolymers are thermoplastic elastomers or are conjugated diene based copolymers with another type of polymer, such as styrene and isobutylene.
25 The copolymers may be a random or a block; di-sequenced; multi-sequenced, or a statistical copolymer. Suitable elastomers include NR, SBR, SB and SBS. The potential for compatibilizing these high molecular weight elastomers of widely varying properties in bituminous compositions is another primary advantage of the present invention.

30 The elastomers which can be used include those having a molecular weight (MW) range from about 45,000 to about 750,000, preferably about

150,000 to about 450,000. These polymeric elastomers are available from a variety of commercial sources.

Such elastomers may be present in the bituminous compositions of the invention in an amount of about 8 to about 13 wt% of the total composition, preferably about 10 to about 12 wt%, depending on the end use to which the composition is put.

The quantity of elemental sulfur which is employed in the invention, generally varies from about 0.05 to about 0.2 wt%, preferably about 0.1 to about 0.15 wt%, based on the amount of bitumen in the composition prior to filing with mineral filler. A corresponding quantity of an alternative cross-linking agent may be used.

According to the present invention, there is a difference in the quantity of reagent required when a different type of cross-linking reagent is used. Following the inventive procedure, with a certain type of reagent involved, a fixed loading relative to the elastomer dispersed system needs to be defined to achieve modified bituminous compositions having significantly improved high temperature performance without loss of flexibility at low temperature. Such performance can be achieved without cross linking but at higher polymer loadings in the corresponding non-cross-linked system. The compositions or formulations are adjusted accordingly in terms of reagent load level, if a different reagent type is used, in order to achieve the desired performance of the modified bitumen.

EXAMPLES

This invention is illustrated by the following Examples:

Example 1:

This Example is an example of the process of the invention and of the compositions attainable thereby.

In this Example, the elastomer modifier used was a tri-block copolymer (SBS: Fina 411, a high molecular weight of star-type sequence SB connection structure). The cross-linking reagents selectively used were two different types of reagents, namely elemental sulfur and phenol-aldehyde resin (marketed by TexPar). The compositions and testing results are shown in Table I below.

The compositions were prepared using the following procedure: SBS was fully dispersed and mixed into bitumen using a Polytron mixer at a temperature range about 185°C for about 60 minutes. The cross-linking reagent was quickly dispersed into the elastomer dispersed bitumen mixture at a fixed amount, depending on the type of the reagent used (see formulations in Table I) and mixing was carried on for about 45 minutes. Then, the agitation was stopped and the temperature was maintained at above 150°C to about 5°C below the mixing temperature for about 60 minutes. Finally, the mixing was continued at the stated mixing temperature again for 15 to 30 minutes to end up with the desired finished product.

As may be seen from Table I, a shift in the amount of reagent was required when a different type of cross-linking reagents was used. With elemental sulfur as the cross-linking reagent involved, a fixed load to the elastomer dispersed system was defined at 0.1% by wt to achieve a modified bituminous composition having a clearly improved temperature performance without loss of flexibility property at low temperature with respect to the corresponding non-cross-linked system. With phenol-aldehyde resin based cross-linking reagent, a fixed load to the elastomer-dispersed system was defined at 0.15% by wt to achieve the same targeted performance.

Example 2:

This Example is an example of conventional elastomer modification of bitumen.

In this Example, the elastomer modifier used was the same type as in Example 1. The same cross-linking reagents from Example 1 were also used.

The compositions were prepared using the conventional procedure: SBS was dispersed, followed by addition of the reagent and mixed in bitumen at the same processing temperature using the Polytron mixer for about 1 or 2 hours. The process also involved the procedure based on the recent prior art using incremental loading technique of reagent and/or SBS at the same processing temperature using Polytron mixer for the same period of time.

The compositions or formulations and testing results are shown in Table II below.

The results set forth in Tables I and II show that acceptable performance in terms of softening point, (high temperature stiffness) and cold flexibility can be achieved at significantly lower polymer loadings than in the prior art, as demonstrated in the case of IS-2, IS-4 and ID-2. All comparative examples that
5 used a polymer loading of less than 12% failed one or the other of the criteria, as did Inventive Examples with excessive cross-linking reagent IS-3 and ID-2. Note also that the quantity of cross-linking agent needed depends on the reagent. In addition, by comparison of Table II samples IS-4, IS-5, IS-2 and ID-3, it can be seen that the performance criteria are retained in the presence of filler.

TABLE I – INVENTIVE EXAMPLE

Ingredient/Code	CI-1	CI-2	IS-1	IS-2	IS-3	IS-4	IS-5	ID-1	ID-2	ID-3
Bitumen (B 200)	88	90	89.95	89.9	89.85	89.4	68.77	89.85	89.8	69.1
SBS	12	10	10	10	10	10.5	8.08	10	10	7.69
Sulfur	-	-	0.05	0.1	0.15	0.1	0.08	-	-	-
Phenol-aldehyde resin	-	-	-	-	-	-	-	0.2	0.15	0.12
Filler (limestone)	-	-	-	-	-	-	23.08	-	-	23.1
PERFORMANCE										
Viscosity at 180°C	1,500	1025	1073	1302	1555	1460	4115	1507	1237	3250
Softening Point, °C	120	114	115	120	124	123	123	121	120	120
Penetration at 25°C	-	-	-	-	-	-	46	-	-	47
Cold Flexibility-25°C	P	P	P	P	F	P	P	F	P	P

TABLE II – COMPARATIVE EXAMPLE

Ingredient/Code	CC-1	CC-2	CS-1	CS-2	CD-2	CD-3
Bitumen (B 200)	88	90	89.95	89.8	89.85	89.8
SBS	12	10	10	10	10	10
Sulfur	-	-	0.05	0.2	-	-
Phenol-aldehyde resin	-	-	-	-	0.15	0.2
PERFORMANCE						
Viscosity at 180°C	1,500	1,025	1740	1930	1310	1507
Softening Point, °C	120	114	115	124	114	121
Cold Flexibility, °C						
-20°C			F	F		P
-25°C	P	P	F	F	P	F

Example 3:

Modified bituminous roofing membranes have been prepared using the sulfur-reacted SBS-filler modified bitumen system, in which a polyester reinforcement mat (width/thickness: 100 mm/1.4mm) is used as the carrier and the top ply of the membrane surfaced with slate granules. The SBS-filler modified binder was coated on the carrier at a rate of approximately 3,600 g/m². The compositions and results of the roofing membranes set forth in Table III prove that acceptable performance in terms of softening point, flow resistance at 100C for 2 hours and cold bend temperature can be achieved at significantly lower polymer loading levels, in fact over 15% less polymer by wt. of the bitumen, as compared to conventional processing.

TABLE III – Modified Bituminous Membranes

Modified Bitumen Composition (%)	Conventional	Inventive-A	Inventive-B
Bitumen (B 200)	71.85	66.25	68.79
SBS	9.63	7.77	8.07
Sulfur	-	0.074	0.077
Limestone	25.91	25.91	23.06
Membrane Performance	Conventional SBS modified Membrane	Inventive SBS modified Membrane	Inventive SBS modified Membrane
Flow resistance @ 100C for 2 hours	Pass	Pass	Pass
Softening Point, °C	116	117	115
Cold Flexibility, -25°C	Pass	Pass	Pass

SUMMARY OF THE DISCLOSURE

In the summary of this disclosure, the present invention provides novel bituminous compositions used to produce roofing membranes having the desired characteristics of stiffness at high temperatures and cold flexibility, using cross-linked elastomeric polymer modifiers at a significantly lower proportion of such polymer, as well as a novel procedure for the preparation of said compositions. Modifications are possible within the scope of this invention.

CLAIMS

1. A roofing membrane having cold flexibility below about -20°C and high flow resistance above about 110°C, comprising a matrix-filled fibrous substrate and a filled elastomer-modified bituminous composition comprising about 10 to about 30 wt% of said composition of a mineral filler and a bituminous composition comprising bitumen and about 8 to 13 wt% of said bitumen of an elastomer having a conjugated diene structure cross-linked to an extent to permit a reduction of about 10 to 20 wt% in the amount of elastomer in the bituminous composition for the same low and high temperature properties or a concomitant improvement in low and high temperature properties at the same amount of elastomer.
2. The roofing membrane of claim 1 wherein said elastomer is employed in an amount of about 10 to 12 wt%.
3. The roofing membrane of claim 1 wherein said filler is employed in an amount of about 15 to about 25 wt%.
4. The roofing membrane of claim 1 wherein said elastomer is a styrene-butadiene-styrene polymer.
5. The roofing membrane of claim 1 wherein said elastomer is cross-linked using a cross-linking agent in a minimum amount such that the desired high temperature stiffness level is achieved at the lower amount of elastomer and in a maximum amount with the low temperature flexibility is not impaired at the lower amount of elastomer.
6. A method of forming a roofing membrane comprising a filled bituminous composition, which comprises:
 - (a) fully dispersing into bitumen an elastomer having a conjugated diene structure in an amount of about 8 to about 13 wt% of the bitumen,
 - (b) dispersing a cross-linking reagent for said elastomer in a predetermined amount depending on the reagent used,
 - (c) permitting said cross-linking reagent to cross-link said elastomer while minimizing the incorporation of air into the composition,

- (d) blending a mineral filler in an amount of about 10 to about 30 wt% of the composition to provide a filled bituminous composition, and
 - (e) forming a roofing membrane from said filled bituminous composition having about 10 to 20 wt% less elastomer in the bitumen for the same low and high temperature properties or a concomitant improvement in low and high temperature properties for the same amount of elastomer.
7. The method of claim 6 wherein said cross-linking agent is elemental sulfur and is used in an amount of about 0.05 to about 0.2 wt%
8. The method of claim 7 wherein the amount of elemental sulfur employed is about 0.1 to about 0.15 wt%.
9. The method of claim 6 wherein said cross-linking agent is phenol-formaldehyde and is used in an amount of about 0.1 to about 0.25 wt%
10. The method of claim 9 wherein the amount of phenol-formaldehyde used is about 0.15 to about 0.20 wt%.
11. The method of claim 6 wherein said elastomer is used in an amount of about 10 to about 12 wt%.
12. The method of claim 6 wherein said filler is employed in an amount of amount of 15 to about 25 wt%.

INTERNATIONAL SEARCH REPORT

A. CLASSIFICATION OF SUBJECT MATTER IPC 7 D06N5/00 E04D5/06 C08L95/00		International Application No PCT/CA 00/00069		
According to International Patent Classification (IPC) or to both national classification and IPC				
B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) IPC 7 D06N E04D C08L				
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched				
Electronic data base consulted during the international search (name of data base and, where practical, search terms used)				
C. DOCUMENTS CONSIDERED TO BE RELEVANT				
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.		
X	EP 0 730 006 A (GRACE W R & CO) 4 September 1996 (1996-09-04) column 2, line 46 - line 57; claims column 3, line 55 - column 4, line 18 column 4, line 55 - column 5, line 18 column 6, line 26 - line 52 ---	1-8, 11, 12		
A	US 5 322 867 A (KLUTTZ ROBERT Q) 21 June 1994 (1994-06-21) column 9, line 15 - line 22; claims ---	1-6, 11, 12		
A	EP 0 317 025 A (SHELL INT RESEARCH) 24 May 1989 (1989-05-24) page 4, line 15 - line 17; claims 1-10; examples ---	1-8, 11, 12		
-/--				
<input checked="" type="checkbox"/> Further documents are listed in the continuation of box C. <input checked="" type="checkbox"/> Patent family members are listed in annex.				
* Special categories of cited documents :				
<table style="width: 100%; border: none;"> <tr> <td style="width: 50%; vertical-align: top;"> "A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier document but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed </td> <td style="width: 50%; vertical-align: top;"> "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. "&" document member of the same patent family </td> </tr> </table>			"A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier document but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. "&" document member of the same patent family
"A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier document but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. "&" document member of the same patent family			
Date of the actual completion of the international search <div style="text-align: center;">16 May 2000</div>	Date of mailing of the international search report <div style="text-align: center;">30/05/2000</div>			
Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016	Authorized officer <div style="text-align: center;">Pamies Ollé, S</div>			

INTERNATIONAL SEARCH REPORT

International Application No

PCT/CA 00/00069

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US H1484 H (COLLINS JAMES H) 5 September 1995 (1995-09-05) the whole document ----	1,2,4-8, 11
A	GB 2 038 848 A (ELF UNION) 30 July 1980 (1980-07-30) the whole document ----	1,2,4-8, 11
A	DD 289 077 A (ZEITZ HYDRIERWERK) 18 April 1991 (1991-04-18) -----	1,2,5-7, 11

INTERNATIONAL SEARCH REPORT

Information on patent family members

In. (ional Application No

PCT/CA 00/00069

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0730006	A	04-09-1996	AU 4447296 A SG 52565 A	05-09-1996 28-09-1998
US 5322867	A	21-06-1994	US 5278207 A DE 69309952 D DE 69309952 T WO 9411443 A EP 0667886 A JP 8503237 T	11-01-1994 22-05-1997 14-08-1997 26-05-1994 23-08-1995 09-04-1996
EP 0317025	A	24-05-1989	AT 88488 T DE 3880441 A DE 3880441 T JP 1165666 A JP 2672987 B US H876 H	15-05-1993 27-05-1993 09-09-1993 29-06-1989 05-11-1997 01-01-1991
US H1484	H	05-09-1995	NONE	
GB 2038848	A	30-07-1980	FR 2440967 A AT 369778 B AT 718479 A BE 879847 A BR 7907255 A CA 1137243 A CH 643282 A DE 2945365 A DK 472979 A ES 485814 A IT 1127205 B JP 1317989 C JP 55069650 A JP 58031107 B NL 7908230 A,B, NO 793609 A,B, SE 437529 B SE 7909260 A	06-06-1980 25-01-1983 15-06-1982 03-03-1980 08-07-1980 07-12-1982 30-05-1984 22-05-1980 10-05-1980 16-05-1980 21-05-1986 29-05-1986 26-05-1980 04-07-1983 13-05-1980 12-05-1980 04-03-1985 10-05-1980
DD 289077	A	18-04-1991	NONE	